

Adfil SF 86

Hook end steel fibre



Technical data sheet

Product description

Polymer	Density	Melting Point	Ignition temperature
Steel	7,8 kg/dm ³	- °C	-

Properties

Physical Properties	Standard	Performance	Tolerance
Equivalent Diameter	EN 14889-1:2006	0,75 mm	+/-0,04 mm
Length	EN 14889-1:2006	60 mm	+/-3 mm
Aspect ratio	EN 14889-1:2006	80	+/- 8
Number of fibres per kg		4600	
Mechanical Properties	Standard	Performance	Tolerance
Elastic Modulus	EN 14889-1:2006	200000 MPa	- MPa
Tensile strength	EN 14889-1:2006	1225 MPa	+/-92 MPa
Effect on consistency of concrete	Standard	Performance	Dosage
Vebe Time	EN 14889-1:2006	6,3 s	9 kg
Control concrete	EN 14889-1:2006	6 s	
Effect on strength of concrete	Standard	Performance	Dosage
Strength @CMOD - 0,5mm	EN 14889-1:2006	1,8 N/mm ²	9 kg
Strength @CMOD - 3,5mm	EN 14889-1:2006	1,6 N/mm ²	
Plastic Shrinkage reduction	ASTM C1579-13	-	-
CE regulation	Standard	Performance	
Class	EN 14889-1:2006	II	

Advantages

The product will enhance the toughness of the concrete and alleviate the need for steel mesh or steel fibres when used with the appropriate design and at the recommended dosage.

Mixing instructions

When adding fibres into a cementitious product careful attention must be taken in the batching and mixing procedure in order to achieve optimum results. If you need further details on the recommended mixing instructions, please consult a member of the ADFIL team.

Storage

Fibres must be stored on a clean surface in dry conditions, undercover and away from the possibility of damage.